



## FICHA TÉCNICA:

# TUBO TERMORRETRÁCTIL POLIOLEFINA PARED FINA SIN ADHESIVO CONTRACCIÓN 2:1 TRPF200°C



**REFERENCIA:** TRPF200 - medida - color

- Temperatura de trabajo: -55°C ~ 200°C
- Temperatura de contracción: >175°C
- Flexible, auto extingüible.
- UL 224 VW-1
-  US C-UL
-  RoHS libre de halógenos.

Property	Test method	Standard
Tensile strength (MPa)	ASTM D2638	≥8.5
Ultimate Elongation (%)	ASTM D2638	≥250
Tensile strength after heat aged (MPa)	250°C x 168h	≥200
Ultimate Elongation after heat aged (%)	250°C x 168h	≥200
Longitudinal change (%)	ASTM D2671	-5%~+5%
Flammability	ASTM D2671 C method	VW-1
Voltage withstand	UL 224, 2500V, 60s	No breakdown
Heat shock	UL 224 250°C x 4hrs	No cracks, flowing or dripping
Dielectric strength(KV/mm)	ASTM D2671	≥7.9
Volume resistivity (Ω.cm)	IEC 60093	≥1X10 <sup>9</sup>